

you can **RELY** on



www.cementaid.com

SPECIFICATION FOR

ANTI-GRAFFITI PROTECTION

GraffeX*

REQUIREMENT:

An invisible, high performance anti-graffiti impregnation for interior & exterior natural / architectural concrete, masonry, and render surfaces, providing graffiti-protection and surface preservation without altering original or natural appearance

PRODUCT TO USE:

GraffeX* Anti-Graffiti Impregnation

EFFECTS:

GraffeX*s advanced "super-slippery" molecules penetrate several millimetres into the surface of concrete and masonry substrates and affix / bind chemically to the underlying calcium silicate, leaving the surface able to "breathe", with little or no change to its natural appearance and/or texture.

GraffeX*s double impregnation resists penetration and adhesion of fresh paint. This inhibits or impairs the bond of common graffiti spray paints, allowing easier and more effective removal, with minimal or no "ghost" marking.

ADVANTAGES:

- Eliminates discolouration, "mottling", delamination and maintenance of barrier coatings.
- Non film-forming - virtually invisible once applied, with little or no change in appearance,
- Inhibits penetration and adhesion of most common graffiti paints
- Allows safer, easier, faster and superior removal from the surface and in depth, using commercial water-based cleaning agents.
- Effective removal of a range of graffiti paints, with zero or minimal "ghost" marking or residue of the graffiti.
- Can be re-applied without marking.
- Sterilises the substrate to resist mould & fungus.
- **GraffeX*** is highly water repellent and will resist wetting of the substrate. This protects against not only graffiti, but also against efflorescence, pollution, dirt & grime from marring the appearance of the substrate.
- Lasting protection; ~ 5-7 years exterior, 8-10 interior
- Maintains clean, new appearance & high building value

PREPARATION:

All surfaces should be clean, dry and free from dust, dirt, oils, grease, curing compounds, paints and other coatings, efflorescence, and laitance before applying.

APPLICATION:

CEMENTAID GraffeX* should be applied onto the clean, DRY masonry surface to achieve maximum absorption in two, separately applied flood-on impregnations, that allow a 150mm run-down of material from the application point. Apply with a brush, roller or very low pressure sprayer (preferred, 1 - 2 psi; no "misting"), allowing 4 or more hours between applications.

Coverage of **GraffeX*** is approximately 2 - 6 m²/litre/coat, depending on porosity. Coverage guide;

Concrete and cement render	Not less than 1 litre per 3-6 sq. metres
Texture and wire cut bricks	Not less than 1 litre per 4.5 sq. metres
Concrete block	Not less than 1 litre per 2-3 sq. metres
Pressed clay brickwork/pavers	Not less than 1 litre per 5.0 sq. metres
Sandstone	Not less than 1 litre per 2.0 sq. metres
Limestone	Not less than 1 litre per 1.5 sq. metres
Terracotta or cement tiles	Not less than 1 litre per 5.0 sq. metres

NOTES: Dense or smooth substrates may require less material than above on second coat, to avoid over-application/surface accumulation. Extremely porous substrates like split concrete block, faux bricks, etc., may require more than two flooding impregnations to achieve effective saturation. May cause slight darkening of white or light coloured substrates. A trial area is recommended to be conducted first to verify coverage and appearance, etc. Re-apply single coat if surface water-repellence is removed following harsh or repeated cleaning abrasion. Do not use solvent-based cleaners to remove graffiti.

GraffeX* is not recommended for painted, glazed, polished or other non-porous surfaces.

SPECIFICATION FOR CHOSEN AREAS:

"All surfaces (specify areas) to be protected against graffiti by a double saturation impregnation with Cementaid **GraffeX*** Anti-Graffiti Impregnation in strict accordance with manufacturer's instructions."

Two applications are required for anti-graffiti protection to walls up to approx. 2 metres high. Cementaid recommend the remaining facades / areas 'out of reach', also be kept clean and pristine to match the graffiti-protected areas over time by a single impregnation of **CEMENTAID GraffeX***

(Alternatively to reduce cost, use the compatible **Cementaid DRIWAL P6**, to preserve the non-graffiti protected areas in similarly new appearance.)

PRECAUTIONS:

GraffeX* liquid is flammable.

NO SMOKING. NO NAKED FLAMES.

Observe all usual precautions with solvents.

Use only under well ventilated conditions.

Refer to Material Safety Data Sheet for **GraffeX***

Do not use in areas where solvent odours may enter building ventilation air-intakes or adjacent structures, or

affect stored foodstuffs or other materials. Do not apply in windy conditions or allow contact with plants or vegetation.



AUSTRALIAN OWNED EXPORTERS TO THE WORLD

INDUSTRIAL FLOOR SPECIFICATIONS • CONCRETE WATERPROOFING & CORROSION-PROOFING ADMIXTURES
OIL & SOLVENT PROOFING • SURFACE TOUGHENING & DUSTPROOFING • ANTI-CORROSION IMPREGNATIONS
RAPID HARDENING • RETARDING • GEL CONTROL AGENT • MORTAR AND DAMPCOURSE ADMIXTURES, etc.

The information and recommendations herein are, as a result of experience and testing, accurate to the best of the seller's knowledge. However, as the proposed use and the circumstances surrounding such use are not known to the seller, it does not guarantee or warrant the product's suitability in any particular instance and shall not be liable for any loss or damage consequent upon any use whatsoever unless the seller has otherwise stipulated the product's suitability for a particular use in writing signed by a Director of the seller.

TECHNICAL SERVICE OFFICES

ADELAIDE

Tel: (08) 8346 9711

Fax: (08) 8346 9977

CEMENTAID (SA & NT) Pty Ltd

ACN: 089 037 749

70 Chief Street

Brompton SA 5007

BRISBANE

Tel: (07) 3276 7388

Fax: (07) 3276 7399

CEMENTAID (QLD) Pty Ltd

ACN: 009 716 018

1/86 Boyland Avenue

Coopers Plains QLD 4108

MELBOURNE

Tel: (03) 9890 0487

Fax: (03) 9890 6223

CEMENTAID (VIC) Pty Ltd

ACN: 004 518 889

15 Clarice Road

Box Hill VIC 3128

PERTH

Tel: (08) 9470 5858

Fax: (08) 9470 5999

CEMENTAID (WA) Pty Ltd

ACN: 000 477 476

200 Star Street

Carlisle WA 6101

SYDNEY

Tel: (02) 9810 0725

Fax: (02) 9810 4164

CEMENTAID (NSW) Pty Ltd

ACN: 000 366 549

44 Alberto Street

Lilyfield NSW 2040