

you can RELY on



MORTAR DAMP-PROOFING ADMIXTURE (BLACK)

SPECIFICATION FOR

CALBLACK*

REQUIREMENT:

Damp-proofing for brick mortar (black colour)

PRODUCT TO USE:

Cementaid CALBLACK

HOW TO SPECIFY:

"All mortar (specify damp-proof course) shall be integrally waterproofed by the addition of Cementaid Calblack Dampcourse Admixture".

The mix shall consist of 1 part fresh Portland Cement to 2 parts sand mixed with water and containing Cementaid Calblack at the rate of one (1) litre per 40Kg bag of cement. **DO NOT USE LIME.**

"The dampcourse must finish with a minimum of 12mm thickness, throughout, or alternatively lay the Calblack mortar for two (2) consecutive horizontal courses with perpendiculars between. Trim and rod joints to a smooth, dense finish".

EFFECTS:

Produces a dense, black mortar, permanently proofed against rising damp, protection which outlasts the life of normal brickwork.

WHERE RECOMMENDED:

All masonry construction at ground level.

PACKAGING:

205 Litre, 20 Litre, 5 Litre, 1 Litre

NOTE:

STIR WELL BEFORE USE

CALBLACK Dampcourse is not a mortar colourant, and will fade with UV exposure over time. To minimise UV exposure, coloured mortars should be struck back from the brick surface and/or rodded hard to bring cement to the surface.



Australian owned

INDUSTRIAL FLOOR SPECIFICATIONS • CONCRETE WATERPROOFING & CORROSION-PROOFING ADMIXTURES
 OIL & SOLVENT PROOFING • SURFACE TOUGHENING & DUSTPROOFING • ANTI-CORROSION IMPREGNATIONS
 RAPID HARDENING • RETARDING • GEL CONTROL AGENT • MORTAR AND DAMPCOURSE ADMIXTURES, etc.

The information and recommendations herein are, as a result of experience and testing, accurate to the best of the seller's knowledge. However, as the proposed use and the circumstances surrounding such use are not known to the seller, it does not guarantee or warrant the product's suitability in any particular instance and shall not be liable for any loss or damage consequent upon any use whatsoever unless the seller has otherwise stipulated the product's suitability for a particular use in writing signed by a Director of the seller.

TECHNICAL SERVICE OFFICES

ADELAIDE
 Tel: (08) 8346 9711
 Fax: (08) 8346 9977
CEMENTAID (SA & NT) Pty Ltd
 ACN: 089 037 749
 70 Chief Street
 Brompton SA 5007

BRISBANE
 Tel: (07) 3276 7388
 Fax: (07) 3276 7399
CEMENTAID (QLD) Pty Ltd
 ACN: 009 716 018
 1/86 Boyland Avenue
 Coopers Plains QLD 4108

MELBOURNE
 Tel: (03) 9890 0487
 Fax: (03) 9890 6223
CEMENTAID (VIC) Pty Ltd
 ACN: 004 518 889
 15 Clarice Road
 Box Hill VIC 3128

PERTH
 Tel: (08) 9470 5858
 Fax: (08) 9470 5999
CEMENTAID (WA) Pty Ltd
 ACN: 000 477 476
 200 Star Street
 Carlisle WA 6101

SYDNEY
 Tel: (02) 9810 0725
 Fax: (02) 9810 4164
CEMENTAID (NSW) Pty Ltd
 ACN: 000 366 549
 44 Alberto Street
 Lilyfield NSW 2040

EXPORT SERVICE & PRODUCTION: CEMENTAID International, 80 O'Neill Street, Leichhardt NSW 2040 Tel: (02) 9810 0725 Fax: (02) 9810 4164 www.cementaid.com * Reg. Trade mark