

you can **RELY** on



www.cementaid.com

## SPECIFICATION FOR

# BONDING AGENT FOR CONCRETE, RENDERS & PLASTERING

# CALBOND\*

### REQUIREMENT:

Bonding to brick, concrete or masonry, without roughening or hacking. Bonding agent for interior renders and toppings, as well as for bonding concrete at concrete construction joints, etc.

### PRODUCT TO USE:

## CALBOND

### HOW TO SPECIFY:

All surfaces (state areas) shall be prepared for plastering/rendering by application of a liberal coat of **CALBOND** which shall be allowed to dry to a "tacky" condition (10 – 20 minutes) before applying render or plaster. Consult manufacturer for details of surface cleaning, etc.

### EFFECTS:

**CALBOND** forms a plastic "key" into the surface pores of the base masonry, which when not fully dry will partially re-dissolve in the damp render or plaster. When set and dried, the whole sets into a hard, tough unit strongly assisting firm adhesion of the surface render. Fully compatible with all CEMENTAID products.

### WHERE RECOMMENDED:

All rendering onto non-roughened surfaces, including integrally waterproofed concrete.

Repair of cracks and faults in masonry.

As admixture in mortar or concrete mix, where elasticity and toughness are required

NOTE: For service under wet areas or wetting drying conditions, Cementaid WELDCRETE is recommended to be used instead.

### FOR NEW FLOOR TOPPINGS

A slurry of **CALBOND** and cement mixed in the proportions of 2 parts **CALBOND**, 2 parts cement and 1 part water, when applied liberally on a clean surface will assist adhesion of applied toppings.

All toppings must be well cured.



Australian owned

INDUSTRIAL FLOOR SPECIFICATIONS • CONCRETE WATERPROOFING & CORROSION-PROOFING ADMIXTURES  
OIL & SOLVENT PROOFING • SURFACE TOUGHENING & DUSTPROOFING • ANTI-CORROSION IMPREGNATIONS  
RAPID HARDENING • RETARDING • GEL CONTROL AGENT • MORTAR AND DAMPCOURSE ADMIXTURES, etc.

The information and recommendations herein are, as a result of experience and testing, accurate to the best of the seller's knowledge. However, as the proposed use and the circumstances surrounding such use are not known to the seller, it does not guarantee or warrant the product's suitability in any particular instance and shall not be liable for any loss or damage consequent upon any use whatsoever unless the seller has otherwise stipulated the product's suitability for a particular use in writing signed by a Director of the seller.

### TECHNICAL SERVICE OFFICES

#### ADELAIDE

Tel: (08) 8346 9711  
Fax: (08) 8346 9977

CEMENTAID (SA & NT) Pty Ltd  
ACN: 089 037 749  
70 Chief Street  
Brompton SA 5007

#### BRISBANE

Tel: (07) 3276 7388  
Fax: (07) 3276 7399

CEMENTAID (QLD) Pty Ltd  
ACN: 009 716 018  
1/86 Boyland Avenue  
Coopers Plains QLD 4108

#### MELBOURNE

Tel: (03) 9890 0487  
Fax: (03) 9890 6223

CEMENTAID (VIC) Pty Ltd  
ACN: 004 518 889  
15 Clarice Road  
Box Hill VIC 3128

#### PERTH

Tel: (08) 9470 5858  
Fax: (08) 9470 5999

CEMENTAID (WA) Pty Ltd  
ACN: 000 477 476  
200 Star Street  
Carlisle WA 6101

#### SYDNEY

Tel: (02) 9810 0725  
Fax: (02) 9810 4164

CEMENTAID (NSW) Pty Ltd  
ACN: 000 366 549  
44 Alberto Street  
Lilyfield NSW 2040