

you can **RELY** on



www.cementaid.com

SPECIFICATION FOR

NON-SHRINK GROUT (CONCRETE OR MASONRY)

CALGROUT NO. 7

REQUIREMENT:

CALGROUT NO. 7 is a non-shrink grout which can be used at flowing consistency without bleed or segregation. It is also non-metallic and does not result in rusting or discolouration.

HOW TO SPECIFY:

All concrete grouting or mortars shall be **CEMENTAID CALGROUT NO. 7** mixed with water to the desired consistency then rammed or flowed into place.

CHARACTERISTICS:

Flowable, easy placed non-shrink grout which attains high early and ultimate strengths. It also does not contain chlorides, iron filings or aluminium powder.

The degree of shrinkage/expansion will depend, to some extent, on curing, but will usually be less than $\pm 0.02\%$ longitudinal expansion under restrained conditions.

NOTE:

CALGROUT NO. 7 should be thoroughly cured for 7 days to produce best effects. Water curing is preferred, but if not practical, a **CALCURE** curing membrane is advised.

WHERE RECOMMENDED:

- Precise final positioning of column and machine bases.
- Grouting of rock anchors with greater bond between grout and rock surface.
- Filling tie rod holes.
- Grouting joints between precast concrete units, so as to maintain specified spacing.
- Setting handrails, bolts, seats, etc.
- Pressure grouting repairs.

MIXING & COVERAGE:

A 25kg bag of **CALGROUT NO. 7** will require approximately 4.25 litres of water to produce 11 litres of pourable, non-shrink grout. Final setting time at 30 degrees C is approximately 4 hours and 10 minutes.

TYPICAL STRENGTHS:

Days	1	3	7	28	90
MPA	39.5	47.0	54.5	61.5	73.0



INDUSTRIAL FLOOR SPECIFICATIONS • CONCRETE WATERPROOFING & CORROSION-PROOFING ADMIXTURES
OIL & SOLVENT PROOFING • SURFACE TOUGHENING & DUSTPROOFING • ANTI-CORROSION IMPREGNATIONS
RAPID HARDENING • RETARDING • GEL CONTROL AGENT • MORTAR AND DAMPCOURSE ADMIXTURES, etc.

The information and recommendations herein are, as a result of experience and testing, accurate to the best of the seller's knowledge. However, as the proposed use and the circumstances surrounding such use are not known to the seller, it does not guarantee or warrant the product's suitability in any particular instance and shall not be liable for any loss or damage consequent upon any use whatsoever unless the seller has otherwise stipulated the product's suitability for a particular use in writing signed by a Director of the seller.

TECHNICAL SERVICE OFFICES

ADELAIDE

Tel: (08) 8346 9711

Fax: (08) 8346 9977

CEMENTAID (SA & NT) Pty Ltd

ACN: 089 037 749

70 Chief Street

Brompton SA 5007

BRISBANE

Tel: (07) 3276 7388

Fax: (07) 3276 7399

CEMENTAID (QLD) Pty Ltd

ACN: 009 716 018

1/86 Boyland Avenue

Coopers Plains QLD 4108

MELBOURNE

Tel: (03) 9890 0487

Fax: (03) 9890 6223

CEMENTAID (VIC) Pty Ltd

ACN: 004 518 889

15 Clarice Road

Box Hill VIC 3128

PERTH

Tel: (08) 9470 5858

Fax: (08) 9470 5999

CEMENTAID (WA) Pty Ltd

ACN: 000 477 476

200 Star Street

Carlisle WA 6101

SYDNEY

Tel: (02) 9810 0725

Fax: (02) 9810 4164

CEMENTAID (NSW) Pty Ltd

ACN: 000 366 549

44 Alberto Street

Lilyfield NSW 2040

EXPORT SERVICE & PRODUCTION: CEMENTAID International, 80 O'Neill Street, Leichhardt NSW 2040 Tel: (02) 9810 0725 Fax: (02) 9810 4164 www.cementaid.com

* Reg. Trade mark