

you can **RELY** on



www.cementaid.com

SPECIFICATION FOR

LB9 *

**ACRYLIC MASONRY GLAZE
& PENETRATING SEALER**

LB9*

REQUIREMENT:

- Sealing & protection of external concrete slab / car park areas, driveways etc. against dusting as well as resistance to penetration & staining by oil or grease, etc.
- Long-term protection of brickwork, pavers, roof and wall tiles, limestone and where a long-lasting, subdued glaze is required while highlighting natural colour / appearance.
- Removal of efflorescence.
- To seal exposed aggregate / architectural masonry surfaces and highlight finish.

HOW TO SPECIFY:

"All surfaces to be thoroughly cleaned & dry, free of oil, grease or other contaminants. Brush down to remove all loose foreign materials. Then apply one or two coats of Cementaid **LB9** Glazing Liquid (allow 2-6 hours between coats). Apply at the rate of 4-5 m² per litre, depending on porosity. Coverage for 2nd coat if required, at rate of 6-8 m² per litre".

Where a non-slip, high-traction surface is especially important, use Cementaid CALGRAINS trowelled into the surface of fresh concrete during placing and finishing. For existing floors where additional traction / anti-slip is required, specify **LB9 Non-Slip Grade**.

LB9 is best applied by brush, short nap lambswool roller or low-pressure knapsack spray. Equipment should be cleaned with solvent based thinners such as Xylene (available from Cementaid). Drying time, light foot traffic approx 2 hours, Motor Vehicles minimum 24-48 hours.

LB9 is fully compatible with Cementaid CALCURE CR. Use of other curing membranes may impair effectiveness, therefore use water or CALCURE CR. If concrete is to be pre-treated with DIAMITE, use water or damp curing only.



Australian owned

INDUSTRIAL FLOOR SPECIFICATIONS • CONCRETE WATERPROOFING & CORROSION-PROOFING ADMIXTURES
OIL & SOLVENT PROOFING • SURFACE TOUGHENING & DUSTPROOFING • ANTI-CORROSION IMPREGNATIONS
RAPID HARDENING • RETARDING • GEL CONTROL AGENT • MORTAR AND DAMPCOURSE ADMIXTURES, etc.

EFFECTS:

A high gloss impregnation & surface sealer which dissolves most types of efflorescence and brings out the natural colour of masonry and tiles etc.

LB9 is UV stable and resists penetration, staining and subsequent corrosion from oils, grease, juices, sugars etc, **LB9** treated floors are easy to clean and require virtually no maintenance.

Effective life, exterior vertical surfaces 12-15 years: Trafficable slabs 5-8 years or more, depending on traffic. **LB9** is available in Clear Glaze or a range of colours. Surfaces to receive Colour **LB9** must be acid-etched first to provide a textured / roughened surface.

WHERE RECOMMENDED:

External concrete floors/car park areas etc. driveways and pavers, roof and wall tiles exposed aggregate, brickwork, limestone, school and kindergarten walls, where long lasting glaze and surface protection is required.

NOTE:

- LB9** is an acrylic resin in a penetrating solvent and does NOT contain silicone.
- LB9** is UV stable, making it suitable for outdoor use. For sealing interior/covered trafficable areas, Cementaid ROKITE is recommended to be used.
- Maintain good housekeeping – Do not leave spilled materials or abrasives to stand on horizontal treated surfaces. Certain oil products may be able to penetrate or mark **LB9** (e.g. hydraulic fluid). If in doubt, conduct a small trial area first, or contact Cementaid to confirm suitability.

PRECAUTIONS:

LB9 liquid is flammable.



NO SMOKING. NO NAKED FLAMES.

Observe all usual precautions with solvents.

Use only under well ventilated conditions.

Refer to Material Safety Data Sheets for **LB9**.

Do not use in areas where solvent odours may enter building ventilation air intakes or adjacent structures, or affect stored foodstuffs or other materials.

The information and recommendations herein are, as a result of experience and testing, accurate to the best of the seller's knowledge. However, as the proposed use and the circumstances surrounding such use are not known to the seller, it does not guarantee or warrant the product's suitability in any particular instance and shall not be liable for any loss or damage consequent upon any use whatsoever unless the seller has otherwise stipulated the product's suitability for a particular use in writing signed by a Director of the seller.

TECHNICAL SERVICE OFFICES

ADELAIDE

Tel: (08) 8346 9711

Fax: (08) 8346 9977

CEMENTAID (SA & NT) Pty Ltd

ACN: 089 037 749

70 Chief Street

Brompton SA 5007

BRISBANE

Tel: (07) 3276 7388

Fax: (07) 3276 7399

CEMENTAID (QLD) Pty Ltd

ACN: 009 716 018

1/86 Boyland Avenue

Coopers Plains QLD 4108

MELBOURNE

Tel: (03) 9890 0487

Fax: (03) 9890 6223

CEMENTAID (VIC) Pty Ltd

ACN: 004 518 889

15 Clarice Road

Box Hill VIC 3128

PERTH

Tel: (08) 9470 5858

Fax: (08) 9470 5999

CEMENTAID (WA) Pty Ltd

ACN: 000 477 476

200 Star Street

Carlisle WA 6101

SYDNEY

Tel: (02) 9810 0725

Fax: (02) 9810 4164

CEMENTAID (NSW) Pty Ltd

ACN: 000 366 549

44 Alberto Street

Lilyfield NSW 2040