

you can **RELY** on



www.cementaid.com

SPECIFICATION FOR

MORTAR PLASTICISER

SYNLIME*

REQUIREMENT:

Workability and "fattiness" in cement mortar, without use of lime.

PRODUCT TO USE:

SYNLIME Mortar Plasticiser

HOW TO SPECIFY:

All mortar shall be (state sand/cement proportion), with Cementaid **SYNLIME** at the rate of 65 to 125ml per 20kg bag of cement. (Recommended mortar 5:1 or 6:1). Lime water or hydrated lime shall not be used.

EFFECTS:

SYNLIME gives a plastic, workable mix, which remains soft and useable for several hours in the batch, but sets quickly as soon as laid in brickwork. Ultimate strength is greater than for lime/cement mortar. The yield per bag of cement is approximately the same as for a lime/cement mortar, due to the bulking effect of air-entrainment.

WHERE RECOMMENDED:

All mortar and cement render.



AUSTRALIAN OWNED
EXPORTERS TO THE WORLD

INDUSTRIAL FLOOR SPECIFICATIONS • CONCRETE WATERPROOFING & CORROSION-PROOFING ADMIXTURES
OIL & SOLVENT PROOFING • SURFACE TOUGHENING & DUSTPROOFING • ANTI-CORROSION IMPREGNATIONS
RAPID HARDENING • RETARDING • GEL CONTROL AGENT • MORTAR AND DAMPCOURSE ADMIXTURES, etc.

The information and recommendations herein are, as a result of experience and testing, accurate to the best of the seller's knowledge. However, as the proposed use and the circumstances surrounding such use are not known to the seller, it does not guarantee or warrant the product's suitability in any particular instance and shall not be liable for any loss or damage consequent upon any use whatsoever unless the seller has otherwise stipulated the product's suitability for a particular use in writing signed by a Director of the seller.

TECHNICAL SERVICE OFFICES

ADELAIDE

Tel: (08) 8346 9711
Fax: (08) 8346 9977

CEMENTAID (SA & NT) Pty Ltd

ACN: 089 037 749
70 Chief Street

Brompton SA 5007

BRISBANE

Tel: (07) 3276 7388
Fax: (07) 3276 7399

CEMENTAID (QLD) Pty Ltd

ACN: 009 716 018
1/86 Boyland Avenue
Coopers Plains QLD 4108

MELBOURNE

Tel: (03) 9890 0487
Fax: (03) 9890 6223

CEMENTAID (VIC) Pty Ltd

ACN: 004 518 889
15 Clarice Road
Box Hill VIC 3128

PERTH

Tel: (08) 9470 5858
Fax: (08) 9470 5999

CEMENTAID (WA) Pty Ltd

ACN: 000 477 476
200 Star Street
Carlisle WA 6101

SYDNEY

Tel: (02) 9810 0725
Fax: (02) 9810 4164

CEMENTAID (NSW) Pty Ltd

ACN: 000 366 549
44 Alberto Street
Lilyfield NSW 2040